

(19) World Intellectual Property
Organization
International Bureau



549774

(43) International Publication Date
7 October 2004 (07.10.2004)

PCT

(10) International Publication Number
WO 2004/085353 A2

(51) International Patent Classification⁷: C07C 5/09,
B01J 23/44

(21) International Application Number:
PCT/EP2004/003263

(22) International Filing Date: 26 March 2004 (26.03.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
2003/18888 26 March 2003 (26.03.2003) KR
2003/18890 26 March 2003 (26.03.2003) KR
2003/18891 26 March 2003 (26.03.2003) KR
2003/19039 27 March 2003 (27.03.2003) KR

(71) Applicant (for all designated States except US): BASF
AKTIENGESELLSCHAFT [DE/DE]; 67056 Lud-
wigshafen (DE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): MOON, Sang,
Heup [KR/KR]; Gyeongnam Apt. 3-801, Seocho-gu,
Seoul 137-752 (KR). KIM, Woo, Jae [KR/KR]; Sam-
sung Tower Palace E-4706 Dogok 2-dong, Gangnam-gu,
Seoul 135-535 (KR). KANG, Jung, Hwa [KR/KR];
Cheongjin-dong 15, Jongno-gu, Seoul 110-130 (KR).
AHN, In, Young [KR/KR]; Dong-a Heights Apt.
110-1708 Sindang 4-dong, Jung-gu, Seoul 100-761 (KR).

(74) Agent: HÖRSCHLER, Wolfram, J.; Isenbruck Bösl
Hörschler, Wichmann Huhn, Theodor-Heuss-Anlage 12,
68165 Mannheim (DE).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,

GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,
ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), Euro-
pean (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR,
GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI, SK,
TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW,
ML, MR, NE, SN, TD, TG).

Declaration under Rule 4.17:

— as to the applicant's entitlement to claim the priority of the
earlier application (Rule 4.17(iii)) for the following desig-
nations AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BW,
BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ,
EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID,
IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU,
LV, MA, MD, MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ,
OM, PG, PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY,
TJ, TM, TN, TR, TT, TZ, UA, UG, UZ, VC, VN, YU, ZA,
ZM, ZW, ARIPO patent (BW, GH, GM, KE, LS, MW, MZ,
SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ,
BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE,
BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE,
IT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI patent
(BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE,
SN, TD, TG)

Published:

— without international search report and to be republished
upon receipt of that report

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: PALLADIUM-BASED CATALYST FOR SELECTIVE HYDROGENATION OF ACETYLENE

(57) Abstract: The present invention describes a Pd-catalyst, further consisting of La, Ti, Nb, K or Si, which have high ethylene selectivity even after a low temperature reduction in the se-lective hydrogenation of acetylene to ethylene and the production method of the same. A catalyst of the invention consists essentially of 0.05 to 2.0% by weight, based on the supported catalyst, of palladium and one or two metals chosen from the group consist-ing of lanthanum, niobium, titanium, potassium and silicon. The said catalyst is pre-pared by the following procedure: 1) Impregnating a support in aqueous solution of tetra amine palladium hydroxide, followed by drying and calcination; 2) The second and, if necessary, a third metal is impregnated by impregnating the Pd-catalyst in the solution of the metal precursor followed by drying and calcina-tion; 3) The catalyst according to step (2) is then reduced in hydrogen at 200°C to 600°C for 1 to 5 hours.



WO 2004/085353 A2